

ULTRAHIGH TENSILE STRENGTH ELECTRIC RESISTANCE WELDED TUBE AND ITS PRODUCTION

Publication number: JP9104921 (A)

Also published as:

Publication date: 1997-04-22

JP3374659 (B2)

Inventor(s): TOYODA SHUNSUKE; MITSUTSUJI HARUO; OMURA MASAKI

Applicant(s): NIPPON KOKAN KK

Classification:

- international: B21C37/08; C21D8/02; C21D8/10; C22C38/00; C22C38/14; C22C38/18; C22C38/58; B21C37/08; C21D8/02; C21D8/10; C22C38/00; C22C38/14; C22C38/18; C22C38/58; (IPC1-7): C21D8/10; B21C37/08; C21D8/02; C22C38/00; C22C38/14; C22C38/58

- European:

Application number: JP19960146029 19960607

Priority number(s): JP19960146029 19960607; JP19950143207 19950609; JP19950201172 19950807

Abstract of JP 9104921 (A)

PROBLEM TO BE SOLVED: To produce an ultrahigh tensile strength steel tube high in tensile strength, excellent in hydrogen delayed fracture resistance and moreover excellent in corrosion resistance.

SOLUTION: A steel slab contg., by weight, 0.10 to 0.19% C, 0.01 to 0.5% Si, 0.8 to 2.2% Mn, 0.01 to 0.06% Al, 0.005 to 0.03% Nb and 0.0005 to 0.0030% B and contg. $\leq 0.02\%$ P, $\leq 0.003\%$ S, $\leq 0.004\%$ N and $\leq 0.015\%$ Ti is soaked at 1150 to 1300 deg.C and, thereafter, with the Ar3 point or above as the finishing temp., is coiled at 500 to 650 deg.C to form into a hot rolled steel strip, which is subjected to pickling and cold rolling, is subsequently soaked under heating to 800 to 900 deg.C in a continuous annealing furnace, is thereafter rapidly cooled and is moreover subjected to tempering treatment at 150 to 250 deg.C.; This steel strip is subjected to tube making at a width drawing rate Q satisfying $1000 \leq Q/(t/D) < 2 \times 10^4$ to obtain the objective ultrahigh tensile strength steel tube, where $Q(\%) = [(t/D) - 1] \times 100$, t(mm): the sheet thickness and D (mm): the outer diameter of the steel tube.

Data supplied from the esp@cenet database — Worldwide